

CLASSIC Cleanroom Gloves



CS52-WA

9" Nitrile 5.2g | Class (10000/1000), AQL 1.5

PRODUCT SPECIFICATION

Physical Properties

Tensile Strength (MPa)	Min. 14	Unaged
Elongation (%)	Min. 500	
Tensile Strength (MPa)	Min. 14	Aged
Elongation (%)	Min. 400	

LPC : $\leq 7000 (>0.5\mu\text{m})$ | IPA/HEX : $< 35.0\text{mg/g}$
 ESD : $\leq 10^9\text{ohms}$

Dimension (mm) Spec

Cuff	Min. 0.08
Palm	Min. 0.10
Finger	Min. 0.12
	40GP: Max 3000cs
	20GP: Max 1200cs



PRODUCT ATTRIBUTES

Non-Sterile | Full Textured | Ambidextrous | Standard Cuff | Powder Free | Chlorinated | Compatible Nitrile Gloves



Standard/Test Compliances (Complied with IEST)



PS66D

9" Latex 6.6g | Class (1000), AQL 1.5

PRODUCT SPECIFICATION

Physical Properties

Tensile Strength (MPa)	Min. 18	Unaged
Elongation (%)	Min. 650	
Tensile Strength (MPa)	Min. 14	Aged
Elongation (%)	Min. 500	

LPC : $\leq 5000 (>0.5\mu\text{m})$ | IPA/HEX : $< 35.0\text{mg/g}$
 ESD : $\leq 10^{10-12}\text{ohms}$

Dimension (mm) Spec

Cuff	Min. 0.10
Palm	Min. 0.12
Finger	Min. 0.14
	40GP: Max 3000cs
	20GP: Max 1200cs



PRODUCT ATTRIBUTES

Non-Sterile | Full Textured | Ambidextrous | Standard Cuff | Powder Free | Chlorinated | Cleanroom Latex Gloves



Standard/Test Compliances (Complied with IEST)



PL80D
PL80X

12" Latex 8.0g | Class (1000/100), AQL 1.5

PRODUCT SPECIFICATION

Physical Properties

Tensile Strength (MPa)	Min. 18	Unaged
Elongation (%)	Min. 650	
Tensile Strength (MPa)	Min. 14	Aged
Elongation (%)	Min. 500	

LPC : $\leq 3500 (>0.5\mu\text{m})$ | NVR : DI Water $< 1.6\text{mg/g}$
 ESD : $\leq 10^{10-12}\text{ohms}$ | IPA/HEX : $< 35.0\text{mg/g}$

Dimension (mm) Spec

Cuff	Min. 0.10
Palm	Min. 0.12
Finger	Min. 0.14
	40GP: Max 3000cs
	20GP: Max 1200cs



PRODUCT ATTRIBUTES

Non-Sterile | Full Textured | Ambidextrous | Long Cuff | Powder Free | Chlorinated | Cleanroom Latex Gloves



Standard/Test Compliances (Complied with IEST)